

BRE tested to the requirements of prEN15601 – a comparative test and results should be compared with the performance of reference products with known satisfactory wind and driven rain performance. Classic Slate performed better than the chosen reference products.

Slate	Pressure factor (Pa) at a leakage rate of 10g/m ² /5min
Classic slate @ 15°	66.3 Pa
Classic slate @ 22.5°	86.0 Pa
Reference Fibre Cement Slate @ 22.5°	-9.5 Pa
Reference Natural Slate @ 15°	41.1 Pa